



香港標準及檢定中心
The Hong Kong Standards and Testing Centre

Date: 2000-01-14

TEST REPORT

Page 1 of 2

NO: WC100992

APPLICANT: (Code: LIH001)

Lik Hung Metal Works Ltd
G/F 5 Cheung Shun St
Cheung Sha Wan
Kln

Attn: Mr Chan Chi Wah

DESCRIPTION OF SAMPLE(S):

One submitted sample said to be 3 pcs of Cable Ladder made from 2 mm mild steel with hot-dipped galvanized finished.

SAMPLE(S) RECEIVED DATE:

2000-01-03

TESTED DATE:

2000-01-06

INVESTIGATION(S) REQUESTED:

Resistance to corrosion test - stripping test for weight of coating.

METHOD(S) USED:

Ref. BS 729 : 1971 (1986) Appendix A


Anne Chuah, CFD
For Managing Director

Conditions in issuance of Test Report

1. This Report is issued in confidence to the client and it will be strictly treated as such by the Hong Kong Standards and Testing Centre Ltd. It may not be reproduced or further disseminated in any form or by any means, electronic or mechanical, including photocopying, recording, or by any information storage and retrieval system, without the prior written permission of the Hong Kong Standards and Testing Centre Ltd. 2. The client is advised that the Report is issued only for the purpose of providing information to the client and it is not to be used for any other purpose. 3. The Hong Kong Standards and Testing Centre Ltd. will not, without the consent of the client, enter into any discussion of, or correspondence with any third party concerning the contents of the Report. 4. The report refers only to the sample tested and does not apply to the bulk, unless the sampling has been carried out by the Hong Kong Standards and Testing Centre Ltd. and is stated as such in the Report. 5. In the event of the improper use of the report, the Hong Kong Standards and Testing Centre Ltd. reserves the right to withdraw it, and to accept any other remedies which may be appropriate. 6. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Hong Kong Standards and Testing Centre Ltd. 7. The Hong Kong Standards and Testing Centre Ltd. will not be liable for or accept responsibility for any loss or damage whatsoever arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations. 8. Applicants wishing to use the Report in court proceedings or arbitration shall inform the Hong Kong Standards and Testing Centre Ltd. to that effect prior to submitting the sample for testing.

香港新界大埔工業邨大宏街10號
10 Dai Wang Street,
Taipo Industrial Estate,
N.T., Hong Kong
Tel: (852) 2666 1888
Fax: (852) 2664 4353
Homepage: www.hkstdc.com
E-mail: hkstdc@hkstdc.com



香港標準及檢定中心
The Hong Kong Standards and Testing Centre

Date: 2000-01-14

Page 2 of 2

NO: WC100992

TEST RESULT(S):

	<u>Result</u>	<u>Limit</u>
Coating weight.....	489 g/m ²	460 g/m ²

SUMMARY:

The test results of the submitted sample was found to comply with BS 729 : 1971 Appendix A - stripping test for weight of coating.

REMARK:

Limit for Coating weight in accordance with BS729 : 1971		
Category		Minimum average coating weight for any individual test area
Steel articles which are not centrifuged	5mm thick and over	610 g/m ²
	Under 5mm but not less than 2mm	460 g/m ²
	Under 2mm but not less than 1mm	335 g/m ²
Grey and malleable iron castings		610 g/m ²
Threaded work and other articles which are centrifuged		305 g/m ²

***** End of Document *****

Conditions in issuance of Test Report

1. This Report is issued in confidence to the client and it will be strictly treated as such by the Hong Kong Standards and Testing Centre Ltd. It may not be reproduced either in its entirety or in part and it may not be used for advertising. The client to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Hong Kong Standards and Testing Centre Ltd. to his customer, supplier or other persons directly concerned. The Hong Kong Standards and Testing Centre Ltd. will not, without the consent of the client, enter into any discussion of competence with any third party concerning the contents of the Report. 2. This report refers only to the sample tested and does not apply to the bulk, unless the sampling has been carried out by the Hong Kong Standards and Testing Centre Ltd. and is stated as such in the Report. 3. In the event of the improper use of the report, the Hong Kong Standards and Testing Centre Ltd. reserves the right to withdraw it, and to adopt any other remedies which may be appropriate. 4. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Hong Kong Standards and Testing Centre Ltd. 5. The Hong Kong Standards and Testing Centre Ltd. will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations. 6. Applicants wishing to use the Report in court proceedings or otherwise shall inform the Hong Kong Standards and Testing Centre Ltd. to that effect prior to submitting the sample for testing.

香港新界大埔工業邨大老街10號
10 Dai Wang Street,
Taipo Industrial Estate,
N.T., Hong Kong
Tel: (852) 2666 1888
Fax: (852) 2664 4353
Homepage: www.hkstdc.com
E-mail: hkstdc@hkstdc.com